

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: G02C 13/00	A1	(11) International Publication Number: WO 95/23351 (43) International Publication Date: 31 August 1995 (31.08.95)
(21) International Application Number: PCT/US95/02233 (22) International Filing Date: 24 February 1995 (24.02.95) (30) Priority Data: 9403792.6 28 February 1994 (28.02.94) GB 08/379,328 26 January 1995 (26.01.95) US (60) Parent Application or Grant (63) Related by Continuation US 08/379,328 (CIP) Filed on 26 January 1995 (26.01.95) (71) Applicant (for all designated States except US): SOLA INTERNATIONAL INC. [US/US]; 2420 Sand Hill Road, Menlo Park, CA 94025 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): SPECTOR, David, P. [US/US]; 6 Liberty Dock, Sausalito, CA 94965 (US). RAM, A., N., Sunder [US/US]; 22 Dupree Court, Petaluma, CA 94954 (US). (74) Agent: SWISS, Gerald, F.; Burns, Doane, Swecker & Mathis, P.O. Box 1404, Alexandria, VA 22313-1404 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: LENS WAFERS WITH REMOVABLE COATING (57) Abstract Disclosed is a lens wafer suitable for use in preparing a laminated lens which wafer has a coating on at least one surface thereof in the form of a peelable protective film.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

LENS WAFERS WITH REMOVABLE COATING

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to lens wafers and more particularly to a polymer
5 composition for coating at least one surface of the lens wafers in order to
provide a means to clean the wafer as well as to form a protective and
removable film thereon.

State of the Art

10 Eyeglass lenses have traditionally been formed as a single integral body
of glass or plastic. Grinding or molding such lenses to meet the specifications
of a particular prescription requires costly equipment, highly skilled technicians
and is time consuming.

It has recently been found that the fabrication of ophthalmic lenses can
be economically accomplished in a more rapid manner with a laminated lens
15 construction in which two lens wafers are bonded together with a transparent
adhesive. Such lens wafers are described, for example, in U.S. Patent Nos.
5,149,181, 4,867,553, and 4,645,317 and British Patent Application,
publication number 2,260,937A which are incorporated herein by reference in
their entirety.

20 The laminate construction enables assembly of composite lenses having
any of a large number of different combinations of optical corrections from a
relatively small stock of prefabricated lens wafers of different configurations.
Pairing of different combinations of a front surface lens wafer with a back
surface lens wafer can, for example, provide composite lenses having any of a
25 large number of different powers as the power of the lens is the summation of

-2-

the powers of the two wafers. Such combinations provide for a large majority of all of the prescriptions required for clear vision.

Notwithstanding the advantages of using lens wafers in the construction of a composite lens, a problem arises with the use of such lens wafers.

5 Specifically, any contaminates such as dust, dirt, fingerprints and moisture found on the wafer surfaces to be glued will become permanently entrapped at the interface of the wafers in the composite lens upon adhesion of the front wafer to the back wafer resulting in defects in the lens. These defects reduce the optical quality of the finished lens and can ultimately lead to lens rejection.

10 Accordingly, in order to provide a defect-free composite lens, the wafer surfaces to be laminated together (with a transparent adhesive) should be substantially clean of such contaminates. However, since the wafers are invariably handled during composite lens fabrication, it is particularly difficult to avoid contaminates such as fingerprints and dust on the wafer surface
15 interface.

The ability to maintain a contaminant-free surface is also critical if optical coatings such as anti-reflection coatings are to be applied. Again, any surface damage or contamination will be uncorrectable after application of the optical coating.

20 Previous methods known in the art neither address nor are applicable to this problem. For example, U.S. Patent Nos. 3,899,315 and 3,899,314 relate to texture control of glass ophthalmic lenses by use of a protective layer which is removed prior to use. Here, a flat glass lens preform is provided with a thin protective layer of a chemically soluble glass fused thereto. In the
25 manufacturing process, the flat preform is subsequently cut and pressed or slumped to the desired ophthalmic shape and the protective layer subsequently removed by dissolving this in a corrosive reagent, thereby exposing the underlying surface which, while smooth, nevertheless needs to be cleaned. The lens is rendered immediately adaptable to ophthalmic use, without further
30 working (grinding, polishing or cleaning) of the surface. This wet process, however, is not suitable for reagent sensitive molded plastic (e.g.,

-3-

polycarbonates or polymethacrylates) lenses. Furthermore, it has been found that the wet process does not provide a sufficiently clean surface on lens wafers required for laminated ophthalmic lenses.

Another unrelated prior art approach to removing dust and grease from a polymer surface is disclosed in U.S. Patent No. 4,199,375 which describes a method for removing dust and grease from phonograph records by applying a polyvinyl alcohol composition which forms a self-supporting film upon drying. When the film is lifted from the record, dust and grease, which are dissolved in the film, are removed. However, this composition, when applied to plastic lenses or lens wafers, forms films that are difficult to remove.

In view of the above, it would be particularly desirable to provide a means to effectively clean the surface of lens wafers prior to adhering this surface to another surface during fabrication of a laminated lens or application of a coating (e.g., an anti-reflection coating) to the wafer surface.

SUMMARY OF THE INVENTION

This invention is based, in part, on the discovery that formation of a self-supporting removable film on the surface of a plastic lens wafer which does not cross-link to the wafer surface provides an effective method to clean the surface of the lens. Additionally, the removable film provides a level of abrasion protection to the underlying surface.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 illustrates an exploded laminated lens comprising a front lens wafer, a transparent adhesive layer and a rear lens wafer.

Figure 2 illustrates the laminated lens of Figure 1 in combined form which lens is suitable for use in corrective glasses.

-4-

DETAILED DESCRIPTION OF THE INVENTION

This invention is directed to methods and compositions for cleaning lens wafers for use in preparing optically corrective laminated plastic lenses. The methods and compositions of this invention employ a self-supporting removable film on at least one surface of the wafer which film is not cross-linked to the wafer but which film encapsulates therein at least a portion of the contaminants found on the surface of the lens wafer.

Accordingly, in one of its method aspects, this invention is directed to a method of cleaning at least one surface of a lens wafer from contaminants which method comprises:

(a) applying a film forming composition onto at least one surface of a lens wafer, said composition comprising:

- (i) a film forming unmodified polymer, and
- (ii) a compatible solvent;

(b) removing the solvent from said composition to form a self-supporting removable film that coats the surface of the wafer to which it was applied without being cross-linked thereto which film encapsulates therein at least a portion of the contaminants found on the wafer surface prior to application of the composition thereto; and

(c) removing said film from the surface of the wafer.

In another of its method aspects, this invention is directed to a method for reducing defects at the interface of front and back lens wafers in a laminated lens wherein the front and back lens wafers are bonded together at the surfaces interfacing with each other with a transparent adhesive which method comprises:

(a) applying a film forming composition onto the interface surfaces of both the front and back lens wafers, said composition comprising:

- (i) a film forming unmodified polymer; and
- (ii) a compatible solvent;

(b) removing said solvent to form a self-supporting removable film that coats the surface of the wafer to which it was applied without being

-5-

cross-linked thereto which film encapsulates therein at least a portion of the contaminates found on the wafer surface prior to application of the composition thereto;

(c) removing said film from the surface of the wafer;

5 (d) applying a transparent adhesive to at least one of said interface surfaces; and

(e) bonding the front lens wafers to the back lens wafer through the interface surfaces of said wafers to form a laminated lens.

In one of its composition aspects, this invention is directed to a lens wafer suitable for use in preparing a laminated lens, said wafer containing
10 on at least one surface thereof a self-supporting removable film wherein said film is not cross-linked to said wafer surface and further wherein said film encapsulates at least a portion of the contaminates found on the lens surface prior to placement of said film thereon.

15 Upon removal of the film from the lens wafer surface, the contaminates encapsulated with the film are removed from this surface. Preferably, the film has a thickness, in the dry state (after solvent evaporation), of from about 8 to about 50 μm (microns), more preferably from about 8 to about 20 μm , and still more preferably from about 10 to
20 15 μm .

In another of its composition aspects, this invention is directed to a lens wafer suitable for use in preparing a laminated lens said wafer containing on at least one surface thereof a self-supporting removable film wherein said film is prepared by the process which comprises:

25 (a) applying a film forming composition onto a surface of the lens wafer, said composition comprising:

(i) a film forming unmodified polymer; and

(ii) a compatible solvent; and

(b) removing said solvent to form the removable film that coats the
30 surface without being cross-linked thereto.

-6-

In a preferred embodiment, the film forming unmodified polymer comprises a copolymer of vinyl chloride and vinyl acetate. More preferably, the copolymer of vinyl chloride and vinyl acetate comprises from about 75 to about 98 weight percent vinyl chloride and from about 2
5 to about 25 weight percent vinyl acetate. In still a more preferred embodiment, such copolymers have a molecular weight of from about 15,000 to about 70,000.

In still another preferred embodiment, the polymer composition further comprises a second copolymer of vinyl chloride and vinyl acetate
10 that has an average molecular weight of about 40,000 to 50,000 wherein the second copolymer comprises about 80 to 90 weight percent vinyl chloride and about 10 to 20 weight percent vinyl acetate. The polymer composition comprising the first and second copolymers preferably has a weight ratio of the first copolymer to the second copolymer of from about 8:1 to about
15 19:1. A particularly preferred polymer composition comprises about 94 weight percent of the first copolymer and about 6 weight percent of the second copolymer.

In yet another composition aspect, this invention is directed to a composition comprising:

20 (1) from about 60 to about 95 weight percent, based on the total weight of the composition, of a solvent mixture comprising acetone and n-amyl acetate as the compatible solvent;

(2) from about 5 to about 25 weight percent, based on the total weight of the composition, of a film forming unmodified polymer;

25 (3) from about 10 to about 35 weight percent, based on the total weight of solids in the film forming composition, of a plasticizer comprising dipropylene glycol dibenzoate; and

(4) from about 0.1 to about 5 weight percent, based on the weight of the composition, of an anti-static agent.

30 In another of its compositional aspects, the invention is directed to a composition suitable for forming a self-supporting removable polymeric

-7-

film on at least one surface of a lens wafer suitable for forming a composite lens which composition comprises:

- 5 (a) a first copolymer that comprises from about 75 to 98 weight percent vinyl chloride and about 2 to 25 weight percent vinyl acetate and that has an average molecular weight of about 25,000 to 28,000;
- (b) a second copolymer that comprises about 80 to 90 weight percent vinyl chloride and about 10 to 20 weight percent vinyl acetate and that has an average molecular weight of about 40,000 to 50,000
- 10 wherein the weight ratio of said first copolymer to said second copolymer ranges from about 8:1 to about 19:1; and
- (c) a compatible solvent.

Preferably, the compatible solvent is selected from the group consisting of acetone, ethyl acetate, amyl acetate, butyl acetate, and mixtures thereof.

- 15 However, prior to addressing this invention in further detail, the following terms will first be defined:

Definitions

- 20 The term "lens wafer" or "wafer" refers to an article comprising a plastic material which article is either the front or back segment of a composite lens which segments are combined and bonded together by use of a transparent adhesive. Such lens wafers are depicted in Figure 1 as elements 10 and 14. Plastic materials useful in preparation of lens wafers are well known in the art and include, by way of example, polycarbonates, polymethacrylates, and the like. The particular plastic material employed is
- 25 not critical. However, preferred plastic materials are polycarbonates and, in particular, an allyl diglycol carbonate available from PPG Industries, Hartford, Connecticut, USA under the tradename CR-39™.

- 30 The term "transparent adhesives" refers to adhesives suitable for bonding lens wafers together which adhesives are optically transparent in the visible light portion of the spectrum and preferably UV curable. Such

-8-

transparent adhesives are disclosed in U.S. Patent Nos. 5,149,181, 4,857,553, and 4,645,317 and British Patent Application, publication number 2,260,937A. The particular transparent adhesive employed herein is not critical but preferably is a UV curable adhesive sold under the tradename MULTI-CURE 492 available from Dymax, Inc., Torrington, Connecticut, USA.

The term "a film-forming unmodified polymer" refers to a polymer or mixture of polymers, including copolymers, that are soluble or suspendable in a compatible solvent such that upon removal of the solvent a film is formed on the surface to which the polymer solution or suspension was applied and which polymers do not contain sufficient functional groups (and preferably no functional groups) so as to result in cross-linking of the polymer to the lens wafer surface. Cross-linking of the polymer to the lens wafer surface refers to covalent or ionic binding of functional groups on the polymer to complementary functional groups found on the surface of the wafer. Such binding (cross-linking) is particularly detrimental since it inhibits the ability to lift the resulting film off the wafer to leave a clean surface (e.g., without leaving traces of the polymer) without deleteriously affecting the surface of the lens wafer.

Generally, unmodified polymers do not have sufficient reactive moieties, such as hydroxyl, carboxyl, epoxy, or amino functionalities, that could bind (cross-link) with complementary reactive functionalities on the substrate surface thereby forming a covalent or ionic linkage therebetween. For example, it is believed that the hydroxyl functionality will readily cross-link with plastic substrates by forming ester and/or ether bonds with complementary reactive groups on the wafer surface (e.g., carboxyl groups and epoxide groups).

Preferred film forming unmodified polymers have a number average molecular weight of from about 15,000 to about 70,000, preferably 20,000 to 45,000 and most preferably from about 25,000 to about 28,000. The use of polymers having lower molecular weights facilitates the preparation of

high solid content solutions of these polymers in the compatible solvent. High solid contents are particularly desirable in areas where solvent emissions are restricted on the basis that solvent coating techniques are limited to high solid contents.

5 In a particularly preferred embodiment, the film forming unmodified polymer comprises a copolymer of vinyl chloride and vinyl acetate. More preferably, the copolymer of vinyl chloride and vinyl acetate comprises from about 75 to about 98 weight percent vinyl chloride and from about 2 to about 25 weight percent vinyl acetate. In still a more preferred
10 embodiment, such copolymers have a number average molecular weight of from about 25,000 to about 28,000.

 In still another preferred embodiment, the polymer composition further comprises a second copolymer of vinyl chloride and vinyl acetate that has an average molecular weight of about 40,000 to 50,000 wherein the
15 second copolymer comprises about 80 to 90 weight percent vinyl chloride and about 10 to 20 weight percent vinyl acetate. The polymer composition comprising the first and second copolymers preferably has a weight ratio of the first copolymer to the second copolymer of from about 8:1 to about
20 19:1. A particularly preferred polymer composition comprises from about 94 weight percent of the first copolymer and about 6 weight percent of the second copolymer.

 It has been found that the presence of such a second unmodified polymer in the polymer composition produces films with enhanced physical characteristics such as increased tensile properties which facilitate the
25 stripping of the film from the substrate. Specifically, the addition of this second unmodified polymer having a higher average molecular weight than that of the first improves the physical properties of the film.

 When the unmodified polymer comprises vinyl resins such as copolymers of vinyl chloride and vinyl acetate, a preferred solvent
30 comprises a mixture of acetone and n-amyl acetate. The acetone is present from about 60 weight percent to 100 weight percent, and preferably at

-10-

about 95 weight percent of total solvent; the n-amyl acetate is present from 0 weight percent to about 40 weight percent, preferably from about 1 to about 5 weight percent and still more preferably at about 5 weight percent of total solvent. This solvent mixture has the advantage of dissolving the vinyl copolymer at room temperature. The n-amyl acetate, which is a slow-evaporating solvent, facilitates application of the composition to lens substrates and, in particular, allows the composition to flow over the substrate to achieve a uniform coating.

The term "compatible solvent" refers to a solvent or mixture of solvents which dissolve or suspend the film forming unmodified polymer(s) and other components of the polymer composition which solvent is not deleterious to the surface of the lens wafer. Solvents should be sufficiently volatile so that once the polymer composition is applied onto a substrate surface, the solvent can be removed to form the film preferably without the aid of heat and/or vacuum. Additionally, the solvent should preferably have a solvent cleaning affect on the surface of the lens wafer such that at least a portion of the contaminants found on the surface of the lens are dissolved or suspended in the solution (i.e., solvent + film-forming unmodified polymer). Preferred solvents include acetone, ethyl acetate, amyl acetate, butyl acetate, etc., and mixtures thereof.

The term "self-supporting removable film" refers to a polymer film having sufficient tensile strength and modulus such that the film stability (i.e., in a stable film form) is independent of the lens wafer surface to which it is applied and which film does not cross-link with the wafer surface thereby permitting complete peeling therefrom, preferably as a single piece.

The term "contaminants" refer to exogenous materials found on the interface surface of a lens wafer which can become entrapped at the interface of the wafers in a laminated lens resulting in defects to the lens. Such contaminants include, by way of example, dust, dirt, fingerprints (including oils associated therewith), moisture, etc.

-11-

Formulation

This invention is directed to the discovery that the formation of a self-supporting removable film on the surface of the lens wafer provides an effective means to dissolve and/or encapsulate at least a portion of the contaminants on the surface of the film. Upon removal of the film from the lens wafer surface, the contaminants dissolved and/or encapsulated within the film are removed from this surface. The film provides the additional advantage of protection from abrasion for the surfaces of the wafer covered by the film.

Specifically, Figure 1 is an exploded view of the elements used to produce a laminated lens 1. Transparent adhesive layer 12 is used to bond the front lens wafer 10 to rear lens wafer 14. Viewing the lens from left to right, the rear surface 16 of front lens wafer 10 and the front surface 18 of rear lens wafer 14 are the interface surfaces for each wafer in the bonded lens. Figure 2 illustrates the composite (laminated) lens 1 in assembled form.

In this invention, it is desirable to clean at least a portion of the contaminants on the interface surfaces 16 and 18 of front and back wafers 10 and 14 respectively prior to bonding these wafers together with the transparent adhesive layer 12. Specifically, cleaning is accomplished by first applying a composition comprising a solvent solution or suspension of a film forming unmodified polymer that forms a self-supporting and removable film when applied to the surface of the plastic lens wafer, subsequent removal of the solvent to form the removable film and then, at some point in time subsequent thereto, removal of the film.

In this composition, the compatible solvent is typically employed in an amount of from about 60 to about 95 weight percent of the total weight of the film-forming composition and preferably from about 70 to about 80 weight percent. The use of lower amounts of compatible solvent is preferred when emission of solvent to the atmosphere is of concern.

-12-

The film forming unmodified polymer is employed in this composition in an amount of from about 5 to about 25 weight percent, based on the total weight of the composition, and preferably from about 15 to about 23 weight percent.

5 In a preferred embodiment, the polymer employed in the film forming composition comprises a copolymer comprising about 86 percent vinyl chloride and 14 percent vinyl acetate and having an average molecular weight of about 27,000. In another embodiment, the polymer composition, further comprises a second copolymer comprising about 90 percent vinyl
10 chloride and 10 percent vinyl acetate and having an average molecular weight of about 44,000. The second copolymer is preferably present at from 5 to 20 percent by weight of total copolymer.

 The film forming composition described above can optionally contain additives such as anti-static agents, plasticizers, anti-oxidants, etc.
15 Plasticizers are typically employed to improve film flexibility and peelability and, when employed, are present at from about 20 percent to about 30 percent by weight based on total solids (i.e., exclusive of solvent) content. Suitable plasticizers include, by way of example, dipropylene glycol dibenzoate, butyl benzyl phthalate, diethylene glycol dibenzoate, and
20 the like. The particular plasticizer employed is not critical but preferably is dipropylene glycol dibenzoate.

 Anti-static agents are typically employed to reduce the amount of static charge created especially when peeling the film from the composite lens. When employed, the composition comprises from about 0.1 to about
25 5 weight percent of the anti-static agent based on the total weight of the composition and preferably about 1.5 weight percent. Suitable anti-static agents include, by way of example, Glycolube AFA™ (available from Lonza, Inc., Fair Lawn, New Jersey, USA), glycerol monooleate, polyoxyethylene sorbitan monooleate, and the like. Alternatively, after

-13-

peeling the removable film from the wafer surface, the wafer surface can be exposed to a bipolar ionized air shower to reduce static.

The above composition is preferably prepared by the addition of the film forming unmodified polymer to the compatible solvent. The rate of addition is monitored and maintained at a sufficiently slow rate to inhibit lumping of the polymer. Mixing is conventionally conducted in a high shear mixer preferably equipped with a tight fitting cover to prevent solvent loss.

Methodology

In operation, the film forming composition prepared as above is applied to at least one surface of lens wafer suitable for forming a composite lens. Preferably, the film forming composition is applied to the interface surface of both the front and back lens wafers. In one embodiment, the film forming composition is applied only to the interface surfaces of both the front and back lens wafers. In another embodiment, the film forming composition is applied to all of the surfaces of the lens wafer.

Application is typically conducted in a manner to provide substantially uniform application of the film forming composition onto the lens wafer surface. Application means include, by way of example, roll coating, dip coating, painting, spin coating, etc. Application by a spin coating process gives an upper thickness limit of about 20 μm .

In some cases it may be desirable to add solvent to the film-forming composition during active coating of the wafer surface to maintain the desired solvent level. Solvent addition can be either incremental or continuous and compensates for solvent loss during coating.

Sufficient amounts of the film forming composition are applied onto the surface or surfaces of the lens wafer to provide for a film thickness, in the dry state (after solvent evaporation), of from about 8 to about 50 μm (microns), more preferably from about 8 to about 20 μm , and still more preferably from about 10 to 15 μm . Film thickness of at least 8 μm is

-14-

necessary to insure that the film is strong enough to exhibit good peelability. As is apparent, a thicker film will also afford greater abrasion resistance.

5 The coating should be coextensive with the surface(s) of the lens wafer so that after solvent removal, a film is formed which is closely juxtaposed to the wafer surface and remains attached until it is peeled off and the lens wafer is ready for use. Accordingly, attachment is made by proximate location of the film coextensive with the surface of the wafer. There is, however, no chemical binding, whether covalent or ionic,
10 between the film and the wafer and, accordingly, the film is peelable.

The methodology employed to form the film results in a cleaning effect on the wafer surface upon removal of the film. Without being limited to any theory, it is believed that the solvent employed in the film forming composition suspends or dissolves a portion of the contaminants
15 when applied to the surface of the wafer. Upon evaporation of the solvent, the contaminants are believed to become encapsulated in the film and, upon film removal, a cleaning effect of the wafer surface is achieved.

In addition to cleaning the wafer surface, the removable film also provides abrasion protection for the surface to which it was applied.
20 Accordingly, it is advantageous to form the removable film on at least one surface of the wafer at the time of manufacture and remove the film at the time of forming the corrective lens thereupon retaining this film on the surface of the wafer during shipment and storage. However, while less advantageous, this invention also encompasses application of the film to the
25 lens wafer surface immediately prior to forming the corrective lens so as to effectively clean the lens surface prior to lamination. In this embodiment, it may be desirable to repeat application and removal of the film to the surface to provide for higher levels of cleaning.

It is contemplated that the self supported removable film described
30 above can also be employed to clean the surface of any plastic lens, regardless of whether the lens is of laminate construction. Such cleaning

-15-

would be required prior to, for example, application of an anti-reflective coating to the lens. In this embodiment, the lens is first cleaned in the manner described above and then treated with the anti-reflective coating. The cleaning step prior to application of the anti-reflective coating ensure
5 that contaminates on the lens surface are not permanently entrapped into the lens/anti-reflective coating interface. All of the parameters discussed above relating to cleaning of lens wafers would be applicable to the cleaning of the lens itself.

Embodiments of the invention are now described by way of the
10 following non-limiting examples.

In these examples, the following abbreviations have the meanings set forth below. If not defined, the abbreviations have their art recognized meanings.

15 g = grams
min. = minutes
Mn = number average molecular weight
 μm = microns (micrometers)

EXAMPLES

Example 1 describes preparation and application of a film forming
20 unmodified composition to form a protective film on a plastic lens wafer. Example 2 describes the same technique except that the unmodified polymer employed comprises of a mixture of vinyl chloride and vinyl acetate copolymers. Comparative Example A describes films formed from a polymer composition wherein the vinyl chloride and vinyl acetate
25 copolymer has a hydroxyl content of about 2.3 percent. As is apparent, the presence of the hydroxyl groups forms a film that strongly bonds to the substrate and therefor is unsuitable for use as a peelable protective film.

-16-

EXAMPLE 1

441g of a copolymer of vinyl chloride and vinyl acetate having approximately 86 weight percent vinyl chloride and about 14 weight percent of vinyl acetate and a number average molecular weight of about 27,000
5 (available from Union Carbide Chemicals and Plastics Co., Danbury, Connecticut, USA under the tradename UCAR Solution Vinyl Resin VYHH™) was added to a solvent blend comprising 1,330 g acetone and 70 g amyl acetate. The VYHH™ was added slowly under agitation at room temperature and in a sealed container in order to prevent clumping and
10 solvent loss. A high shear mixer was used to provide the required agitation. Dissolution of the copolymer required almost one hour. 150 g of a plasticizer consisting of dipropylene glycol dibenzoate (available under the tradename Benzoflex 9-88™ from Velzicol Chemical Corp., Rosemont, Illinois, USA) was then added to the mixture, and the mixture stirred for
15 five minutes. This was followed by the addition of 9 g of an anti-static agent (available under the tradename Glycolube AFA-1™ from Lonza, Inc., Fair Lawn, New Jersey, USA). The polymer composition was stirred for 10 min. prior to application. The composition comprised about 30 percent solids by weight.

-17-

Table 1 lists the components and proportions in the polymer composition.

TABLE 1

	COMPONENT	WEIGHT (gram)	WEIGHT (percent)	SOLIDS (percent)
5	VYHH™	441	22.05	73.50
	BENZOFLEX 9-88™	150	7.50	25.00
	GLYCOLUBE AFA-1™	9	0.45	1.50
	ACETONE	1330	66.50	0
	AMYL ACETATE	70	3.50	0
10	TOTAL	2000	100	100

The polymer composition of Example 1 was applied to an ophthalmic lens wafer substrate formed of a polymerized allyl diglycol carbonate (available as CR-39™ PPG Industries, Hartford, Connecticut, USA). The composition was applied by spin coating whereby the lens is mounted on a rotatable spindle and rotated at a high speed to disperse the liquid over the moving surface to attain a coating of uniform thickness. The coating was allowed to dry at ambient conditions to form a solid film on the lens wafer. Preferably, the film is about 10 μ m thick.

The film was removed by attaching adhesive tape to an edge region of the substrate and withdrawing the tape from the substrate to peel the film away. The film exhibited good peelability and cleaning effectiveness as it was able to remove surface dust and grease-based contaminants (e.g., fingerprints) without breaking up.

-18-

EXAMPLE 2

The procedure described above in Example 1 was carried out, with the replacement of the single VYHH™ copolymer with a mixture of VYHH™ and UCAR Solution Vinyl Resin VYNS-3™ (also available from
5 Union Carbide Chemicals and Plastics Co., Danbury, Connecticut, USA) which is another vinyl chloride/vinyl acetate copolymer, which comprises about 90 percent vinyl chloride and about 10 percent vinyl acetate and has a number average molecular weight Mn of about 44,000. The proportion of VYHH™ to VYNS-3™ was about 95 percent VYHH™ to 5 percent
10 VYNS-3™, by weight.

The mixture was prepared by adding VYNS-3™ slowly to acetone under agitation for almost one hour until the VYNS-3™ dissolved. After complete dissolution of the VYNS-3™, the VYHH™ was slowly added, requiring also approximately one hour for complete dissolution. Thereafter
15 the plasticizer and anti-static agent were added to the mixture, and the final composition applied to a lens surface by spin coating. The resultant film exhibited particularly good film properties in terms of film tear strength and toughness.

COMPARATIVE EXAMPLE A

20 The procedure of Example 1 was repeated but the copolymer used was a vinyl chloride/vinyl acetate copolymer with vinyl alcohol in the polymer backbone (available as VAGH™ from Union Carbide), and having a vinyl chloride content of about 90 percent, about 4 percent vinyl acetate, with a hydroxyl content of about 2.3 percent and a number average
25 molecular weight of about 27,000.

The film was evaluated for its strippable characteristics from a CR-39™ lens wafer substrate. It was found that the film adhered strongly to the substrate, and could not be stripped therefrom. This is due to cross linking with the plastics lens wafer substrate as a result of the hydroxyl
30 functionality.

-19-

Another aspect of this invention is a lens wafer of the type used in formation of a laminated lens having a coating on at least one surface thereof in the form of a strippable protective film.

5 Still another aspect of this invention is a method of coating a lens wafer of the type used in formation of a laminated lens, comprising:

- a) providing a composition coating; and
- b) applying the composition to at least one surface of the lens wafer by a spin coating process.

10 The subject matter disclosed herein is also found in our priority British Patent Application No. 9403792.6 which is incorporated herein by reference in its entirety.

15 Although only preferred embodiments of the invention are specifically disclosed and described above, it will be appreciated that many modifications and variations of the present invention are possible in light of the above teachings and within the purview of the appended claims without departing from the spirit and intended scope of the invention.

-20-

WHAT IS CLAIMED IS:

1. A method of cleaning at least one surface of a lens wafer from
contaminates which method comprises:

(a) applying a film forming composition onto at least one surface of
5 a lens wafer, said composition comprising:

- (i) a film forming unmodified polymer, and
- (ii) a compatible solvent;

(b) removing the solvent from said composition to form a self-
supporting removable film that coats the surface of the wafer to which it
10 was applied without being cross-linked thereto which film encapsulates
therein at least a portion of the contaminants found on the wafer surface
prior to application of the composition thereto; and

(c) removing said film from the surface of the wafer.

2. A method for reducing defects at the interface of front and back
15 lens wafers in a laminated lens wherein the front and back lens wafers are
bonded together at the surfaces interfacing with each other with a
transparent adhesive which method comprises:

(a) applying a film forming composition onto the interface surfaces
of both the front and back lens wafers, said composition comprising:

- 20 (i) a film forming unmodified polymer; and
- (ii) a compatible solvent;

(b) removing said solvent to form a self-supporting removable film
that coats the surface of the wafer to which it was applied without being
cross-linked thereto which film encapsulates therein at least a portion of the
25 contaminants found on the wafer surface prior to application of the
composition thereto;

(c) removing said film from the surface of the wafer;

(d) applying a transparent adhesive to at least one of said interface
surfaces; and

-21-

(e) bonding the front lens wafers to the back lens wafer through the interface surfaces of said wafers to form a laminated lens.

3. The method according to Claim 1 or Claim 2 wherein the film forming unmodified polymer comprises a vinyl resin.

5 4. The method according to Claim 1 or Claim 2 wherein the film forming unmodified polymer comprises a copolymer of vinyl chloride and vinyl acetate.

10 5. The method according to Claim 4 wherein the copolymer comprises from about 75 to about 98 weight percent vinyl chloride and from about 2 to about 25 weight percent vinyl acetate further wherein said copolymer has a number average molecular weight of from about 25,000 to about 28,000.

15 6. The method according to Claim 5 wherein the copolymer composition further comprises a second copolymer of vinyl chloride and vinyl acetate that has a number average molecular weight of about 40,000 to 50,000 wherein the second copolymer comprises about 80 to 90 weight percent vinyl chloride and about 10 to 20 weight percent vinyl acetate with the weight ratio of the first copolymer to the second copolymer being from about 8:1 to about 19:1.

20 7. The method according to Claim 6 wherein polymer composition comprises from about 94 weight percent of the first copolymer and about 6 weight percent of the second copolymer.

8. The method according to Claim 6 wherein the polymer composition further comprises a plasticizer.

-22-

9. The method according to Claim 8 wherein the plasticizer comprises dipropylene glycol dibenzoate which constitutes from about 10 to about 35 weight percent, based on the total weight of solids in the film forming composition.

5 10. The method according to Claim 9 wherein the polymer composition further comprises an anti-static agent.

11. The method according to Claim 10 wherein the compatible solvent is selected from the group consisting of acetone, ethyl acetate, amyl acetate, butyl acetate, and mixtures thereof.

10 12. The method according to Claim 11 wherein the removable film is from about 8 to about 50 μm thick.

13. A lens wafer suitable for use in preparing a laminated lens said wafer containing on at least one surface thereof a self-supporting removable film wherein said film is not cross-linked to said wafer surface and further
15 wherein said film encapsulates at least a portion of the contaminants found on the lens surface prior to placement of said film thereon.

14. A lens wafer suitable for use in preparing a laminated lens said wafer containing on at least one surface thereof a self-supporting removable film wherein said film is prepared by the process which comprises:

20 (a) applying a film forming composition onto a surface of the lens wafer, said composition comprising:

(i) a film forming unmodified polymer; and

(ii) a compatible solvent; and

(b) removing said solvent to form a self-supporting removable film
25 that coats the surface of the wafer to which it was applied without being cross-linked thereto which film encapsulates therein at least a portion of the

-23-

contaminates found on the wafer surface prior to application of the composition thereto.

15. The lens wafer according to Claim 13 or 14 wherein said film comprises a vinyl resin.

5 16. The lens wafer of Claim 15 wherein the vinyl resin comprises a copolymer of vinyl chloride and vinyl acetate.

10 17. The lens wafer of Claim 16 wherein the copolymer comprises from about 75 to about 98 weight percent vinyl chloride and from about 2 to about 25 weight percent vinyl acetate further wherein said copolymer has a number average molecular weight of from about 25,000 to about 28,000.

15 18. The lens wafer of Claim 17 wherein the copolymer further comprises a second copolymer of vinyl chloride and vinyl acetate that has a number average molecular weight of about 40,000 to 50,000 wherein the second copolymer comprises about 80 to 90 weight percent vinyl chloride and about 10 to 20 weight percent vinyl acetate with the weight ratio of the first copolymer to the second copolymer being from about 8:1 to about 19:1.

19. The lens wafer of Claim 15 wherein the film further comprises a plasticizer.

20 20. The lens wafer of Claim 19 wherein the plasticizer comprises dipropylene glycol dibenzoate.

21. The lens wafer of Claim 20 wherein the film further comprises an anti-static agent.

-24-

22. The lens wafer according to Claim 13 or Claim 14 wherein the film is from about 8 to about 50 μm thick.

23. A composition comprising:

- 5 (1) from about 60 to about 95 weight percent, based on the total weight of the composition, of n-amyl acetate as the compatible solvent;
- (2) from about 5 to about 25 weight percent, based on the total weight of the composition, of a film forming unmodified polymer;
- (3) from about 10 to about 35 weight percent, based on the total weight of solids in the film forming composition, of a plasticizer
- 10 comprising dipropylene glycol dibenzoate; and
- (4) from about 0.1 to about 5 weight percent, based on the weight of the composition, of an anti-static agent.

24. A composition suitable for forming a self-supporting removable polymeric film on at least one surface of a lens wafer suitable for forming a composite lens which composition comprises:

15

- (a) a first copolymer that comprises from about 75 to 98 weight percent vinyl chloride and about 2 to 25 weight percent vinyl acetate and that has an average molecular weight of about 15,000 to 100,000;
- (b) a second copolymer that comprises about 80 to 90 weight percent
- 20 vinyl chloride and about 10 to 20 weight percent vinyl acetate and that has an average molecular weight of about 40,000 to 50,000 wherein the weight ratio of said first copolymer to said second copolymer ranges from about 8:1 to about 19:1; and
- (c) a compatible solvent.

25 25. The composition of Claim 24 wherein said compatible solvent is a mixture of acetone and amyl acetate.

-25-

26. A coating composition for application to lenses or other optical surfaces comprising a vinyl resin which comprises at least one unmodified copolymer of vinyl chloride and vinyl acetate.

1/1



FIG. 1




FIG. 2

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 95/02233

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G02C13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G02C A61L G11B B08B C03C C11D C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,4 636 543 (HELTON) 13 January 1987 see claim 13 ---	23-26
X	File supplier PAJ/JPO & JP-A-4171013 (Michirou shibazaki) 18/6 92 *abstract*	23-26
Y	---	3-22
X	DATABASE WPI Derwent Publications Ltd., London, GB; AN 90-196958 & JP,A,2 129 299 (FUJI GUM) 17 May 1990 see abstract	1,2
Y	---	3-22
X	File supplier PAJ/JPO & JP-A-1176484 (Shunya Kawamoto) 12/7 89 *abstract* --- -/--	1,2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* & * document member of the same patent family

Date of the actual completion of the international search

27 June 1995

Date of mailing of the international search report

7. 02. 95

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Lentz, J

INTERNATIONAL SEARCH REPORT

Intern. Application No.

PCT/US 95/02233

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>DATABASE WPI Derwent Publications Ltd., London, GB; AN 87-183279 & JP,A,62 115 073 (NIPPON SEIKA) 26 May 1987 see abstract</p> <p>---</p>	3-22
A	<p>DE,A,16 69 160 (KILLARNEY) 23 July 1970 see claim 1</p> <p>-----</p>	23-26

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 95/02233

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4636543	13-01-87	NONE	
DE-A-1669160	23-07-70	GB-A- 1140558	

THIS PAGE BLANK (USPTO)